

TYPE:	<b>A thick two-pack, Polyester or Vinyl ester/acrylic glass flake for hand application.</b> Except for viscosity this product has similar properties to the spray applied version of each product.
SUGGESTED USE:	Stripe coating and areas where spray application is impractical.
	LIMITATIONS: See limitations on main product sheets Polyglass, Polyglass VE & VEF.
HEALTH & SAFETY:	Before handling or using this product the material safety data sheet should be read and all precautions observed.
SURFACE PREPARATION:	For optimum performance of these products under immersed conditions, grit blast steel to ISO standard 8501-1 Sa 2½. SSPC-SP 10 or better, prior to application. For full details refer to Corrocoat Surface Preparation SP1.
APPLICATION EQUIPMENT:	Brush or trowel.
APPLICATION:	When used alone two or more coats of Polyglass HA should be applied until a minimum DFT of 650 microns has been achieved, over thickness is not detrimental. When used as a stripe coat a single layer of circa 300um should be applied, or as otherwise specified. (See below for overcoating intervals.)
MIXING RATIO:	Polyglass HA/VEHA can be catalysed by a 2% weight addition of Corrocoat catalyst type P2. Catalyst <b>P1 must not be used</b> in conjunction with hand applied Polyglass.
MIXING PROCEDURE:	Material is supplied in kits, each consisting of the base component (large tin) together with the appropriate amount of catalyst (plastic bottle). Add 1 bottle of catalyst to a tin of base material and agitate with a <b>mechanical</b> mixer for circa 2 minutes. Ensure <b>all</b> material is thoroughly mixed especially the bottom <b>corner of tin</b> .
POT LIFE:	60 minutes at 20°C. Pot life will reduce <b>substantially</b> with increase in temperature and extend with decrease in temperature. Inhibitor is available to extend pot life for hot climates. Mix inhibitor well and before catalyst.
VOLUME SOLIDS:	This material contains volatile liquid convertible to solids. Actual volume solids obtained will vary dependent upon polymerisation conditions. Nominally 99.% of the contents are convertible to solid.
THEORETICAL SPREADING RATE:	2.0m <sup>2</sup> /litre at 500 microns

**PRACTICAL SPREADING RATE:**

1.6m<sup>2</sup>/litre at 500 microns.

**Note:** This information is given in good faith but rate may **vary significantly** dependent upon environmental conditions, the geometry and nature of work undertaken and the skill and care of application. Corrocoat accept no responsibility for any deviation from these values.

**OVERCOATING:**

It is important to observe maximum overcoating times and note these **will vary significantly** with climatic conditions. Overcoating may take place as soon as the previous coat has gelled sufficiently to bear the weight of the next coat and whilst still tacky. Maximum overcoating interval is 72 hours at 20°C for PGHA, 48 hrs for VEHA. For longer intervals than this refer to Corrocoat TSD for advice. Best inter-coat adhesion characteristics are obtained by short overcoating intervals.

Refer to main product data sheets for full information.

**CURING TIMES:**

Tack free: Approx 4 hours at 20°C

Full Cure: 3-4 days at 20°C

Minimum cure before immersion: 24 hours at 20°C

**THINNERS:**

**THIS PRODUCT SHOULD NOT BE THINNED.** The use of solvent thinners will adversely affect performance and under no circumstances must they be used.

**CLEAN-UP SOLVENT:**

Use Methyl Ethyl Ketone or Methyl Iso-butyl Ketone before gelation occurs.

**All values are approximate.**

**Information regarding application of the product is available in the Corrocoat manual. Should further information be required, please consult Corrocoat Technical Services.**

**Reviewed: July 2011**